



## Uses of Bifenthrin 2.5% EC

### **Bifenthrin 2.5% EC**

1. Pre and post construction: Bifenthrin 2.5% EC shall be applied at 0.05% a.i. conc. i.e. 20.0 ml formulated product diluted in 1 liter of water for the control of termites in building during pre and post construction. Treatment should be as per IS 6313 (Part 2):2001 for pre construction chemical treatment and IS 6313 (Part-3): 2001 for post construction treatment of the existing building.

2. Recommendation for use of control of Wood borer (Powder Post Beetle) in plywood, veneer and wood

Use	Method of application	Dosage (a.i.)	Dilution
Plywood	Glue Line Poisoning	10 g/meter <sup>3</sup> of wood	400 ml formulation per meter <sup>3</sup> of wood
	Dipping	0.025% Solution	Mix 01 lit of formulation in 99 lit of water to make 0.025% Solution
Veneer	Dipping	0.025% Solution	Mix 01 lit of formulation in 99 lit of water to make 0.025% Solution
Wood	Dipping /Brushing	0.025% Solution	Mix 01 lit of formulation in 99 lit of water to make 0.025% Solution